

Kappy Grav Coarse / fine

High Quality Exterior Scratched Wall Coatings

DESCRIPTION & USES:

- Kappy Grav is high Quality wall coating based on acrylic co-polymers
- Contains coarse aggregates & selected marble grains to give a decorative scratched/smooth effect .
- For exterior and interior use.
- Kappy Gravi Coarse / Fine is applied over fair face concrete ,cement plasters , wood , steel (after protection against corrosion) .
- There are three different particle size fillers two size used for **kappy Grav Coarse** and one use for **kappy Grav fine**.
- Several scratched designs could be obtained by applying the product in many different ways .
- It is environment friendly product.

Properties :

| | |
|---|---|
| Finish | Scratched rough texture |
| Color | Available in white & several colors |
| Density at 25° | Appox 180,000 CP |
| % Solid content by volume | 73± 3 % |
| Wash ability / Wet Scrub resistance | Washable –Rain Resistant |
| Diluent / thinner | Water |
| Drying time at 25° C and relative humidity 50 % | Touch Dry : 30 min Recoat : 2 – 3 hours Hard Dry : 24 hours |

Instruction for use

1- Surface preparation

- Surface should be clean , solid and non-chalking .

2- Application:

- Use tiba seal coat to prime the surface.
- Mix carefully the content to obtain homogeneous paste.
- Apply a layer of tiba Grav using a stainless steel trowel in thickness equivalent to the size of the coarse grains in the product.
- Pass over with the same trowel to level the layer and remove any excess deposition .
- Allow the product to dry just a little (around 10-15 minutes) , then re-pass over with a clean plastic trowel in vertical movement to obtain vertical scratches (or rotate in movement if circular scratch is desired).this movement of the plastic trowel over the product will cause the sliding of the spherical grains to form Scratched rough texture.
- Dilution : 5 % water if needed.

Note : product should not be applied in direct sun light , strong wind ,and rain or temperature over 40^oc.

Application tools: trowel

Coverage : 2 -3 Kg. / m² for kappy Grav Fine and 3 -4 Kg. / m² for Kappy Grav Coarse depending on surface condition , deposition and losses.

Packing : 20 Kg.

Storage and shelf Life : 10 month in original tightly closed bags / containers away from direct sunlight and excessive heat.

Our recommendation are based on extensive research as well as practical experience However , as the product is often used under condition beyond our control , we cannot guarantee anything but the quality of the product itself We reserve the right to change the given data without notice . for any additional information call customer services department .

